



## MagnaPrint® Bling Range

## Ready to use metallic printing pastes

MagnaPrint® Bling is a ready to use metallic print paste that has excellent shine and elasticity. The paste may be pigmented with MagnaPrint® Eco Pigments to achieve different colours such as Bling Gold & Bronze. Recipes are available upon request.


## **Application**

MagnaPrint® Bling should be printed through a 32 - 61 (86 - 156) mesh screen with rectangular profile squeegees. As the particle size is 10 - 60 micron this should be considered when selecting screen mesh.

When printing as part of a multicoloured design print the MagnaPrint® Bling as the last screen to avoid pick up.

After printing the garment/panel should be cured, ideally for 2<sup>1</sup>/<sub>2</sub> - 3 minutes at 165°C (330°F).

## **SPECIFICATION**



**FABRIC TYPES** Cotton / Poly Cotton blends

Medium 65° Shore

Water resistant emulsion

**CURE TEMPERATURE** 2 - 2<sup>1</sup>/<sub>2</sub> minutes at 165°C

Retardant Gel, Crosslinker 100, Softener TS Conc

In cool place properly closed: >5°C (40°F) <25°C (77°F)

MSDS available upon

Wash off screen using water

and mild detergent 

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.

> MagnaColours® Limited Upper Cliffe Road, Dodworth Business Park, Barnsley, S75 3SP, UK

T: 00 44 (0) 1226 731751 F: 00 44 (0) 1226 731752 E: info@magnacolours.com www.magnacolours.com

Company registered in England No. 01378495, VAT No. GB 997 3172 70